

Aramid Fabric

High Tenacity Series

Style	Weave	Denier	Count <small>[per 10cm]</small>	Weight <small>[g/m²]</small>	Thickness <small>[mm]</small>	Tensile Strength <small>[N/5cm]</small>	
						Warp	Weft
HT 601	Plain	600D	112	155	0.23	6,800	6,800
HT 602	Plain	600D	137	190	0.29	8,300	8,300
HT 840	Plain	840D	105	200	0.3	8,000	8,000
HT 100	Plain	1,000D	85	190	0.3	7,700	7,700
HT 101	Plain	1,000D	112	280	0.43	10,500	12,000
HT 152	2 X 2 Basket	1,500D	120	410	0.62	17,500	17,500

Standard Tenacity Series

Style	Weave	Denier	Count <small>[per 10cm]</small>	Weight <small>[g/m²]</small>	Thickness <small>[mm]</small>	Tensile Strength <small>[N/5cm]</small>	
						Warp	Weft
ST 100	Plain	1,000D	85	190	0.3	7,000	7,000
ST 101	Plain	1,000D	122	280	0.43	10,900	11,400
ST 150	2 X 2 Basket	1,500D	127	445	0.6	16,000	16,000
ST 153	2 X 2 Basket	1,500D	122	425	0.6	15,500	15,500
ST 300	Plain	3,000D	67	460	0.65	17,500	17,500
ST 303	4 X 4 Basket	3,000D	80	554	0.88	20,400	20,400

+ Note : Depending on usage and performance requirements, fabrics may be post-treated

- Scoured
- Laminated
- Water-Repellant Treated
- Dipped